



CC Porcelain Tender Gray 12"x12"

CC PORCELAIN

Unglazed Dot Mounted Porcelain








Snow White
12"x12" Mosaic
U272CC-12M



Tender Gray
12"x12" Mosaic
U261CC-12M




Bone
12"x12" Mosaic
U278CC-12M



Sand
12"x12" Mosaic
U277CC-12M





Taupe
12"x12" Mosaic
U289CC-12M



Black
12"x12" Mosaic
U259CC-12M

Trims

Product		Color	SKU
2"x12" Bullnose		Snow White Tender Gray Sand Bone Taupe Black	U272CC-S886 U261CC-S886 U277CC-S886 U278CC-S886 U289CC-S886 U259CC-S886
2"x12" Cove		Snow White Tender Gray Sand Bone Taupe Black	U272CC-C833 U261CC-C833 U277CC-C833 U278CC-C833 U289CC-C833 U259CC-C833
2"x2" Bullnose Corner		Snow White Tender Gray Sand Bone Taupe Black	U272CC-SC886 U261CC-SC886 U277CC-SC886 U278CC-SC886 U289CC-SC886 U259CC-SC886
2"x2" Cove Outside Corner		Snow White Tender Gray Sand Bone Taupe Black	U272CC-SC813 U261CC-SC813 U277CC-SC813 U278CC-SC813 U289CC-SC813 U259CC-SC813

Technical Specs

Characteristics	Standard	Declared ASTM
Water Absorption	C373	$\leq 0.5\%$
Break Strength	C648	Min. 450
Scratch Hardness	MOH's Scale	5
Chemical Resistance	C650	Unaffected
Frost Resistance	C1026	Resistant
Group	SEE FAQS	4
Deep Abrasion - Unglazed Tiles	C1243	-
PEI - Glazed Tiles***	C1027	4 & 2 (black)
Minimum Bond Strength (PSI)	C482	165
Dynamic Coefficient of Friction (DCOF)	A137.1	≥ 0.42
Shade and Texture Rating	CTDA "V"	V2
Facial Dimensions	C499	Pass
Range of Thickness	C499	Pass
Warpage	C485	Pass
Wedging	C502	Pass

Packaging Info

Size	SF. Per Carton	Pieces Per Carton
12"x12"	10.66	11
2"x12" Bullnose	10.65	66
2"x12" Cove	9.04	56
2"x2" Bullnose Corner	10.65	396
2"x2" Cove Outside Corner	2.69	100